

Jampilen C30S

Homopolymer



Description:

"Jampilen C30S" is a polypropylene homopolymer with good flow properties and is particularly suitable for the extrusion of film yarn, monofilament, cast film and sheet. "Jampilen C30S" combines outstanding processability with good mechanical properties. Film yarn made of "Jampilen C30S" is used for baler twines, packaging twines and ropes. "Jampilen C30S" is well suited for the production of monofilament used for instance in brush and broom filling and technical applications.

Processing Method:

Extrusion (Sheet, film yarn, monofilament)
Cast film

Features:

Good processability
Good mechanical properties
Homopolymer

Typical Applications:

Baler twines, packaging twines and ropes
Brush and broom filling and technical applications
Coextruded film for packaging
Thin sheet for stationery folders
Sheet for thermoforming
Gunny sacks

Approval:

Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	6.0	g/10min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mechanical			
Flexural Modulus	1400	MPa	ASTM D790
Tensile Strength at Yield	32	MPa	ASTM D638
Tensile Elongation at Yield	9	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	40	J/m	ASTM D256
Thermal			
Vicat softening point (10N)	152	°C	ASTM D1525
H.D.T. (0.46 MPa)	84	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	360	hours	ASTM D3012

No. 5, North-Falamak St., Eyyamak Blvd., Farahzadi Blvd., Shahrak-e-Qods., Tehran, 1467715171, Iran.
Tel: +9821-84286, Fax: +9821-88363100
Email: info@ppc.ir
www.jppc.ir



This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.