

Jampilen Z30S

Homopolymer



Description:

"Jampilen Z30S" is a high melt flow homopolymer for the production of CF, BCF and fine denier staple fibers at medium to high spinning speeds and exhibits excellent antigasfading properties.

"Jampilen Z30S" is suitable for nonwoven fabrics for diapers, medical-sanitary applications and wipes. Another typical application is high tenacity continuous filament for straps for backpacks, sport bags, bulk bags and safety belts. Continuous filament with medium tenacity is used for upholstery and sportswear. "Jampilen Z30S" is also suited for the production of bulked continuous filament for carpets.

"Jampilen Z30S" is suitable for food contact.

Processing Method:

Fiber Extrusion (CF, BCF, staple)
Injection molding

Features:

High melt flow
Excellent antigasfading properties
Good processability
Homopolymer

Typical Applications:

Wipes and tissues
Straps for backpacks, sport bags, bulk bags and for safety belts
Upholstery and sportswear
Bulk continuous filament for carpets
Nonwoven staple fiber
Injection molded articles, housewares, etc

Approval:

Food

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	25	g/10min	ASTM D1238
Density	0.9	g/cm ³	ASTM D1505
Mechanical			
Flexural Modulus	1400	MPa	ASTM D790
Tensile Strength at Yield	32	MPa	ASTM D638
Tensile Elongation at Yield	8	%	ASTM D638
Izod Impact Strength (notched) at 23 °C	20	J/m	ASTM D256
Thermal			
Vicat softening point (10N)	152	°C	ASTM D1525
H.D.T. (0.46 MPa)	84	°C	ASTM D648
Accelerated oven ageing in air at 150 °C	150	hours	ASTM D3012

No. 5, North-Falamak St., Eyvanak Blvd., Farahzadi Blvd., Shahrak-e-Qods., Tehran, 1467715171, Iran.
Tel: +9821-84286, Fax: +9821-88563100
Email: info@ppco.ir
www.ppco.ir



This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or processes described.