

LG EVA EA28400

Ethylene Vinyl Acetate Copolymer

Applications

Hot Melt Adhesive

Performance

- Uniform VA Contents and MI
- Excellent compatibility with other raw material of HMA
- Good organoleptic property

Typical properties

Characteristics	Test Method	Unit	Value
Physical ⁽¹⁾			
VA Contents	LG	%	28
Density	ASTM D1505	g/cm³	0.945
MFR(190℃,2.16Kg)	D1238	g/10min	400
Mechanical ⁽²⁾			
Tensile Strength at Break	D638 ⁽³⁾	Мра	3
Elongation at Break	D638 ⁽³⁾	%	900
Hardness			
Shore hardness(Shore A)	D2240	<u> </u>	68
Thermal			
Vicat Softening Point	LG	.€	<40
Melting Temperature	LG	_ ℃	68

- (1) The properties data in this table are typical values, and not guaranteed specification.
- (2) Typical resin property values are measured on a standard compression molded specimens
- (3) Speed of 500 mm/min.

Processing information

EA28400 may be processed on conventional equipment.

For additional sales, order and technical assistance

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932,6613

TS&D TECH Center. Polyolefin

175, Gajeong-ro, Yuseong-gu, Daejeon, 305-343, Korea. Tel. 82-42-860-8378

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user hear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."

وبسایت : www.alfapk.com

ایمیل : info@alfapk.com

تلفن تماس : ۴۴۵۵۴۶۰۰-۲۱

Revised: 01/07/2014

تلفن همراه : ۴۴۳۵۳۴۳-۹۱۲