

Honam EVA VA800
Ethylene Vinyl Acetate Copolymer
Honam Petrochemical Corporation



Prospector

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Good Adhesion • Good Processability
Uses	• Adhesives • Automotive Applications • Coating Applications

Physical

	Nominal Value Unit	Test Method
Density	0.950 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	20 g/10 min	ASTM D1238
Vinyl Acetate Content	28.0 wt%	

Hardness

	Nominal Value Unit	Test Method
Rockwell Hardness	25	ASTM D785

Thermal

	Nominal Value Unit	Test Method
Vicat Softening Temperature	< 40.0 °C	ASTM D1525
Melting Temperature	69.0 °C	

Notes

¹ Typical properties: these are not to be construed as specifications.