

SEETEC EVA VA910
Ethylene Vinyl Acetate Copolymer
Lotte Daesan Petrochemical Corp.



Prospector

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Features	• Good Adhesion • Good Processability
Uses	• Adhesives
Forms	• Pellets

Physical	Nominal Value Unit	Test Method
Density	0.950 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	400 g/10 min	ASTM D1238
Hardness	Nominal Value Unit	Test Method
Durometer Hardness (Shore D)	18	ASTM D2240
Thermal	Nominal Value Unit	Test Method
Vicat Softening Temperature	40.0 °C	ASTM D1525
Melting Temperature	65.0 °C	DSC

Notes

¹ Typical properties: these are not to be construed as specifications.