

Polyamide 66

TECHNICAL DATA SHEET

Material Information: Polyamide 66, reinforced with 30% of glass fiber, heat stabilized, lubricated for injection moulding.

Notes: Eplamid 66 glass fiber reinforced compounds are used in all sectors of industry, offering a good balance of thermal and mechanical properties.

This material is available in natural and colours on request.

TESTS	TEST METHOD	UNIT	VALUES	
			DAM	CONDITIONED

PHYSICAL TESTS

DENSITY (23 °C)	ISO 1183	g/cm ³	1,36	
ASH CONTENT	ISO 3451-4	%	30	
DETERMINATION OF WATER CONTENT	ISO 15512	%	0,2	
MOLD SHRINKAGE - PARALLEL / NORMAL (3 mm)	ISO 294-4	%	0,4/0,8	

MECHANICAL TESTS

TENSILE MODULUS (1 mm/min / 23 °C)	ISO 527-2	N/mm ²	10600	8600
TENSILE STRESS AT BREAK (5 mm/min / 23 °C)	ISO 527-2	N/mm ²	190	140
TENSILE STRAIN AT BREAK (5 mm/min / 23 °C)	ISO 527-2	%	3,5	6
FLEXURAL MODULUS (2 mm/min / 23 °C)	ISO 178	N/mm ²	9100	7100
FLEXURAL STRENGTH (2 mm/min / 23 °C)	ISO 178	N/mm ²	245	190
NOTCHED IZOD IMPACT (23 °C)	ISO 180/1A	kJ/m ²	14	15
UNNOTCHED IZOD IMPACT (23 °C)	ISO 180/1U	kJ/m ²	85	90
NOTCHED CHARPY IMPACT (23 °C)	ISO 179/1eA	kJ/m ²	15	16
UNNOTCHED CHARPY IMPACT (23 °C)	ISO 179/1eU	kJ/m ²	90	95

THERMAL TESTS

MELTING POINT	ISO 3146	°C	260	
HDT/B (120 °C/h - 0,45 Mpa)	ISO 75-2/B	°C	255	
HDT/A (120 °C/h - 1,8 Mpa)	ISO 75-2/A	°C	250	

FLAMMABILITY AND ELECTRICAL PROPERTIES

FLAMMABILITY CLASSIFICATION (0,8 mm) - UL 94	EN 60695-11-10	-	HB	
COMPARATIVE TRACKING INDEX - CTI (SOLUTION A)	EN 60112	V	500	
SURFACE RESISTIVITY	ASTM D257	Ω/sq	1,00E+14	

TEST CONDITIONS

Laboratory conditions are 23 ±2°C and 45-55 % RH.

The information in this data sheet is given in good faith but without warranty. These datas do not release you from the obligation to test our products as to their suitability for the intended processes and uses. The application use and processing of our products and the products manufactured by you are beyond our control. Therefore, entirely your own responsibility. Eplamid, Eplon, Epopen and Epimix are registered trademarks of Epsan Plastik San. Tic. Aş.