

# POE LC670

## Polyolefin Elastomer for Polymer Modification

**Applications** • General purpose thermoplastic elastomer for polymer modification  
• Automotive interior/exterior, Shoe sole, PVEN

**Performance** • Improved impact strength in polypropylene  
• Excellent filler acceptance  
• Available as pellet form  
• Outstanding toughness with flexible performance  
• Reduction of product weight

Resin Properties	Test methods	Units	Values <sup>(1)</sup>
Melt Index, 2.16kg/190 °C	ASTM D 1238	g/10min	5.0
Density @ 23 °C	ASTM D 1505	g/cm <sup>3</sup>	0.870
Mooney viscosity, ML <sub>1+4</sub> @ 121 °C	ASTM D 1646	°C	9

Physical Properties	Test methods	Units	Values <sup>(2)</sup>
Tensile Strength @ Break	ASTM D 638 <sup>(3)</sup>	MPa	5.5
Elongation @ Break	ASTM D 638 <sup>(3)</sup>	%	>1000
Flexural Modulus, 1%	ASTM D 790	Mpa	13
Hardness, Shore A	ASTM D 2240	-	70
Tear Strength, Type C	ASTM D 624	kN/m	38

Thermal Properties	Test methods	Units	Values
Melting Point, DSC	LG Method	°C	58
Glass Transition Temperature	LG Method	°C	-55

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 508 mm/min.



Head Office : NCC/PO Division, LG Chem, Ltd.  
LG Twin Tower 23F, Yeouido-dong, Yeongdeungpo-gu, Seoul 150-721, Korea  
Tel : 82-2-3773-3053, 7184, Fax : 82-2-784-9731~3  
Tech Center : 84, Jang-dong, Yuseong-gu, Daejeon 305-343, Korea  
Tel : 82-42-860-8550, 8549, Fax : 82-42-862-1318

وبسایت : [www.alfapk.com](http://www.alfapk.com)  
ایمیل : [info@alfapk.com](mailto:info@alfapk.com)

تلفن تماس : ۰۲۱-۴۴۵۵۴۶۰۰  
تلفن همراه : ۰۹۱۲-۴۴۳۵۳۴۳