

# LUCEL N109LDS

Injection Molding, POM

## Description

Chemical Resistance

## Application

Copier, Watch, Clock, VCR, Printer Parts, etc.

Properties	Test Condition	Test Method	Unit	Typical Value
<b>Physical</b>				
Specific Gravity		ASTM D792	-	1.41
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	1.8 ~ 2.1
Melt Flow Rate	190 °C/2.16kg	ASTM D1238	g/10min	13
<b>Mechanical</b>				
Tensile Strength, 3.2mm @ Yield	10mm/min	ASTM D638	kg/cm <sup>2</sup>	625
Tensile Elongation, 3.2mm @ Break	10mm/min	ASTM D638	%	60
Flexural Strength, 6.4mm	2.8mm/min	ASTM D790	kg/cm <sup>2</sup>	920
Flexural Modulus, 6.4mm	2.8mm/min	ASTM D790	kg/cm <sup>2</sup>	26,000
IZOD Impact Strength, 6.4mm (Notched)	23 °C	ASTM D256	kg·cm/cm	6.5
Rockwell Hardness	R-Scale	ASTM D785	-	82
<b>Thermal</b>				
Heat Deflection Temperature, 6.4mm (Unannealed)	18.6kg 4.6kg	ASTM D648	°C °C	110 160
Flammability 0.8mm 1.6mm 2.5mm 3.2mm		UL94	class class class class	
<b>Electrical</b>				
Dissipation Factor 1MHz		ASTM D150	-	3.8
Surface Resistivity		ASTM D257	Ohm	1*10 <sup>16</sup>
Volume Resistivity	23 °C	ASTM D257	Ohm·cm	1*10 <sup>14</sup>
Dielectric Strength, 1mm	23 °C	ASTM D149	kV/mm	24

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection moulded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Updated : 9-Nov-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.