



Jampilen Z30S

Homopolymer

Description:

"Jampilen Z30S" is a high melt flow homopolymer for the production of low denier BCF, CF and staple fibers at medium to high spinning speeds. "Jampilen Z30S" offers a high homogeneity, stable extrusion and excellent processability on both short and long spinning lines. This grade allows a high stretch ratio and gives tough and resilient fibers.

"Jampilen Z30S" is widely used for the production of bulked continuous filament for carpet face yarns. Another major application is the production of high tenacity continuous filament for straps for backpacks, handles for big bags and safety belts. Continuous filament with medium tenacity is used for upholstery, sportswear and heavy duty clothing.

"Jampilen Z30S" is also suitable for the production of low denier staple fibres for the thermobonding. "Jampilen Z30S" is suitable for food contact.

Processing Method:

Extrusion (BCF, CF and staple fibers)

Features:

High melt flow
Excellent processability
Homopolymer

Typical Applications:

Bulked continuous filament for carpet face yarns
High tenacity continuous filament for straps for backpacks
Handles for big bags and safety belts
Upholstery, sportswear and heavy duty clothing
Low denier staple fibres for the thermobonding

Approval:

Food

Alfa Polymer Kimia

TYPICAL PROPERTIES	VALUE	UNIT	METHOD
Physical			
Melt Flow Rate (230 °C, 2.16kg)	25	g/10min	ISO 1133
Density	0.9	g/cm ³	ISO 1183
Mechanical			
Flexural Modulus	1550	N/mm ²	ISO 178
Tensile Strength at Yield	35	N/mm ²	ISO R 527
Tensile Elongation at Yield	13	%	ISO R 527
Izod Impact Strength (notched) at 23 °C	3	kJ/m ²	ISO 180
Hardness Shore D	72	points	ISO 868
Thermal			
Vicat softening point (9.8N)	155	°C	ISO 306/A
H.D.T. (0.46 Mpa)	118	°C	ISO 75/B
Accelerated oven ageing in air at 150 °C	360	hours	ISO 4577

4th Floor, No. 3, Taban St., Africa Blvd., Tehran, Iran.
Tel: +9821-82124002-5, Fax: +9821-82124006
Email: info@jppc.ir
www.jppc.ir

This data and information is considered to be correct and offered in good faith as a guide. But we do not warrant or otherwise guarantee the merchantability, fitness for a particular purpose or suitability of this information, products or process described.

PPCO-DS-31/01 Oct 07