

## Z 30 S

Z 30 S is a high melt flow homopolymer for the production of low denier BCF, CF and staple fibers at medium to high spinning speeds.

Z 30 S offers a high homogeneity, stable extrusion and excellent processability on both short and long spinning lines

This grade allows a high stretch ratio and gives tough and resilient fibers.

Z 30 S is widely used for the production of bulked continuous filament for carpet face yams. Another major application is the production of high tenacity continuous filament for straps for backpacks, handles for big bags and safety belts.

Continuous filament with medium tenacity is used for upholstery, sportswear and heavy duty dothing. Z 30 S is also suitable for the production of low denier staple fibres for thermobonding.



وبسایت : www.alfapk.com info@alfapk.com تلفن تماس : ۴۴۵۵۴۶۰۰-۲۱۰ تلفن همراه : ۴۴۳۵۳۴۳-۹۱۲



| PROPERTIES                            | METHOD (b) | UNIT              | TYPICAL VALUE (a) |
|---------------------------------------|------------|-------------------|-------------------|
| Physical properties                   |            |                   |                   |
| Melt flow rate (230°C, 2.16 kg)       | ISO 1133   | Dg / min          | 25                |
| Density                               | ISO 1183   | g/cm <sup>3</sup> | 0.9               |
| Mechanical properties                 |            |                   |                   |
| Flexural modulus                      | ISO 178    | N/mm <sup>2</sup> | 1550              |
| Tensile strength at yield             | ISO R 527  | N/mm <sup>2</sup> | 35                |
| Elongation at yield                   | ISO R 527  | %                 | 13                |
| IZOD impact strength (notched)at 23°C | ISO 180    | kJ/m <sup>2</sup> | 3                 |
| Hardness Shore D                      | ISO 868    | Points            | 72                |
| Thermal properties                    |            |                   |                   |
| Vicat softening point (9,8 N)         | ISO 306/A  | °C                | 155               |
| H.D.T. (0.46 Mpa)                     | ISO 75/B   | °C                | 118               |
| Accelerated oven ageing in air        | ISO 4577   | hours             | 360               |
| (forced circulation) at 150°C         |            |                   | _/_               |

- OZ 30 S is suitable for food contact.
- a) Values shown are averages and are not to be considered as product specification These values may shift slightly as additional data are accumisted.
- b) ISO test methods are the lates under the societys current procedures.

All specimens are prepared by injection moulding.



وبسایت : info@alfapk.com ایمیل : info@alfapk.com تلفن تماس : ۴۴۵۵۴۶۰۰-۲۱۰ تلفن همراه : ۴۴۳۵۳۴۳-۲۱۲۰